

CARBO S-Ti 2

CARBO T-Ti 2

International standards

	S = solid wire	T = bare rod
Material No.	~ 3.7036	
DIN 1737	SG Ti 2	WSG Ti 2
AWS SFA-5.16	ER Ti 2	ER Ti 2

Approvals

Application notes

Titanium MIG/TIG wire for welding of pure Titanium and Titanium alloys with good elongation and medium strength.

Mechanical properties of all-weld-metal

(typical values)

Tensile strength R _m N/mm ²	Yielding strength R _{p0,2} N/mm ²	Elongation A ₅ %	Hardness HB
400-540	275	20	180

Weld metal analysis

(typical, wt %)

C	Fe	N	H	O ₂	Ti
< 0,08	< 0,25	< 0,05	< 0,013	< 0,18	balance

Gas types EN 439

S = solid wire

T = bare rod

pure

Gasconsum

flash
shielding

12-14 l / min
1-2 l / min

Current

= +

= -

Diameter mm
Welding amps (A) min.
(A) max.

1,5	2,0	2,4	3,2	4,0
35	70			
60	80			

coils, weight

Rev. 001/13